

BAM Bundesanstalt für Materialforschung und -prüfung

in co-operation with the Committee of Chemists of the GDMB
Gesellschaft der Metallurgen und Bergleute e.V.

Certified Reference Material

BAM-M384a

Pure Copper

Certified Values

Element	Mass fraction ¹⁾ in mg/kg	Uncertainty ²⁾ in mg/kg
Ag	10.7	0.4
As	5.4	0.8
Bi	6.16	0.25
Cd	4.1	0.2
Co	3.64	0.16
Fe	2.7	0.5
Mn	0.22	0.03
Ni	6.1	0.5
Pb	11.7	1.1
Sb	5.4	0.5
Se	5.8	0.6
Sn	2.6	0.5
Te	9.3	0.5
Zn	5.3	0.5

¹⁾ Unweighted mean value of the means of accepted sets of data (consisting of at least 3 but usually 6 single results), each set being obtained by a different laboratory and/or a different method of measurement. The values are traceable to the SI (Système International d'Unités) via calibration using pure metals or substances of known stoichiometry.

²⁾ Estimated expanded uncertainty U with a coverage factor of $k=2$, corresponding to a level of confidence of approx. 95 %, as defined in the Guide to the expression of uncertainty in measurement, (GUM, ISO/IEC Guide 98-3:2008).

Sample description

The Reference Material is available in the form of discs (38 mm diameter and 30 mm height).

Indicative values

Element	Mass fraction ¹⁾ in mg/kg	Uncertainty ²⁾ in mg/kg
Al	< 1.5	
Cr	< 0.2	
Mg	< 0.2	
P	< 1.5	
S	4.6	1.4
Si	< 2.5	
Ti	< 1	
Zr	0.1	0.07
¹⁾ Values were not certified, but given as indicative values, when the number of accepted data sets was considered to be too low (< 5) or when the uncertainty from the inter-laboratory certification was considerably larger than the expected range. The values are traceable to the SI (Système International d'Unités) via calibration using pure metals or substances of known stoichiometry. ²⁾ Estimated expanded uncertainty U with a coverage factor of $k = 2$, as defined in the Guide to the expression of uncertainty in measurement, (GUM, ISO/IEC Guide 98-3:2008).		

Informative Value

One laboratory determined oxygen and found 0.26 % mass fraction.

Recommended Use

The CRM is intended for establishing or checking the calibration of optical emission and X-ray spectrometers for the analysis of samples of similar matrix composition. The minimum sample size for wet chemical analysis is 0.5 g.

Participating Laboratories

Allgemeine Gold- und Silberscheideanstalt, Pforzheim, Germany
Aurubis AG, Hamburg, Germany
BAM Bundesanstalt für Materialforschung und -prüfung, Berlin, Germany
Codelco, Chuquicamata, Chile
Diehl Metall Stiftung & Co KG, Röthenbach, Germany
Institut Glörfeld, Willich, Germany
Johannes Gutenberg-Universität Mainz, Institut für Kernchemie, Mainz, Germany
Montanwerke Brixlegg, Brixlegg, Austria
Outokumpu VDM, Werdohl, Germany
Umicore Precious Metals., Hoboken, Belgium
Wieland-Werke AG, Vöhringen, Germany

Means of Accepted Data Sets

Mass fraction in mg/kg
Certified values

Indicative values

Line no.	Ag	As	Bi	Cd	Co	Fe	Mn	Ni	Pb	Sb	Se	Sn	Te	Zn	Al	Cr	Mg	P	S	Si	Ti	Zr
1	9.45	4.40	---	3.92	3.18	1.99	0.20	---	8.63	---	---	1.80	8.10	---	0.03	0.015	0.03	0.06	< 1	0.10	0.05	0.02
2	10.17	4.63	5.65	3.94	3.42	2.50	0.21	5.17	10.34	5.00	4.81	2.35	8.40	---	0.32	0.018	0.03	0.13	3.34	< 1	0.06	0.03
3	10.32	4.79	6.00	4.00	3.50	2.67	0.21	5.50	10.75	5.08	5.41	2.50	8.83	4.98	< 1	0.022	0.08	0.21	4.20	1.83	0.08	< 0.05
4	10.48	5.00	6.09	4.00	3.53	2.74	0.23	5.90	11.49	5.19	5.50	2.63	9.00	5.00	< 1	0.026	0.15	< 1	4.80	---	---	0.15
5	10.58	5.28	6.15	4.04	3.59	2.75	0.23	6.23	11.58	5.24	5.52	2.65	9.50	5.08	1.30	0.193	< 1	< 1	---	< 1	< 1	0.15
6	10.68	5.67	6.18	4.05	3.69	2.78	---	6.26	11.70	5.25	5.70	2.77	9.67	5.17	---	< 1	< 1	1.37	---	< 1	< 1	0.17
7	10.90	5.87	6.32	4.06	3.69	3.03	< 1	6.27	12.43	5.29	5.91	2.83	9.73	5.28	---	< 1	< 1	1.52	---	< 1	< 1	---
8	11.00	5.90	6.33	4.11	3.69	3.14	< 1	6.28	12.97	5.42	6.00	2.85	10.00	5.28	---	< 1	< 1	---	---	---	< 1	---
9	11.00	5.92	6.33	4.22	3.82	---	< 1	6.47	13.32	5.47	6.28	3.04	10.17	5.47	---	< 1	---	---	---	---	---	< 1
10	11.05	6.70	6.45	4.30	3.95	---	< 1	6.48	13.33	5.53	7.12	---	10.17	5.49	---	---	---	---	---	---	---	---
11	11.07	---	---	---	4.00	---	---	6.75	---	5.73	---	---	---	6.15	---	---	---	---	---	---	---	---
12	11.42	---	---	---	---	---	---	---	---	5.85	---	---	---	---	---	---	---	---	---	---	---	---
13	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
<i>M</i>	10.68	5.42	6.16	4.06	3.64	2.70	0.22	6.13	11.63	5.37	5.80	2.60	9.36	5.32	< 1.5	< 0.2	< 0.2	< 1.5	4.11	< 2	< 1	0.10
<i>s_M</i>	0.53	0.72	0.24	0.12	0.24	0.36	0.10	0.46	1.48	0.27	0.65	0.37	0.74	0.36	---	---	---	---	0.74	---	---	0.08
$\bar{s}_i$	0.26	0.28	0.51	0.12	0.09	0.47	0.04	0.48	0.58	0.48	0.31	0.32	0.63	0.26	---	---	---	---	0.35	---	---	0.07

The laboratory mean values have been examined statistically to eliminate outlying values. Where a " --- " appears in the table it indicates that an outlying value has been omitted (Grubbs 95 %). A data set consists of at least 3 but usually 6 single values of one laboratory.

M : mean of laboratory means

s_M : standard deviation of laboratory means

$\bar{s}_i$: averaged repeatability standard deviation (square root of the mean of laboratory variances)

Note: "< - values" were not included into the calculation of *M* and *s_M*

Analytical Method used for Certification

Element	Line no.	Method
Ag	1, 5	GD-MS
	2, 6, 7, 8, 9, 10, 12	ICP-OES
	3, 11	INAA
	4	ICP-MS
As	1, 2	GD-MS
	3	ICP-MS
	4, 5, 7, 8, 9, 10	ICP-OES
	6	ET AAS
Bi	2	ICP-MS
	3, 6, 7, 10	ICP-OES
	4, 9	ET AAS
	5, 8	GD-MS
Cd	1, 2, 3, 4, 5, 6, 7, 9	ICP-OES
	8	GD-MS
	10	ICP-MS
Co	1, 2, 3, 4, 5, 8, 9, 11	ICP-OES
	7	ICP-MS
	6, 10	GD-MS
Fe	1, 2, 3, 4, 5, 6	ICP-OES
	7	ICP-MS
	8	GD-MS
Mn	1	GD-MS
	2, 3, 7, 8, 9, 10	ICP-OES
	4	ET AAS
	5	ICP-MS
Ni	2, 3, 4, 5, 6, 9, 11	ICP-OES
	8	ICP-MS
	7	GD-MS
	10	ET AAS
Pb	1, 3, 5, 6, 7, 9	ICP-OES
	2, 8	GD-MS
	4	ICP-MS
	10	ET AAS
Sb	2, 3, 5, 8, 11	ICP-OES
	4, 7	INAA
	6	ICP-MS
	9, 12	GD-MS
	10	ET AAS

Element	Line no.	Method
Se	2, 7	GD-MS
	3, 6	ET AAS
	4, 8, 9, 10	ICP-OES
	5	INAA
Sn	1, 8	GD-MS
	2, 4, 5, 7, 9	ICP-OES
	3	ET AAS
	6	ICP-MS
Te	1, 9	GD-MS
	2	INAA
	3, 4, 5, 6, 10	ICP-OES
	7	ICP-MS
	8	ET AAS
Zn	3, 4, 7, 8	ICP-OES
	5, 10	GD-MS
	6	FAAS
	9	ICP-MS
	11	INAA
Al	1	GD-MS
	2, 3, 4, 5	ICP-OES
Cr	1, 4	GD-MS
	2, 5, 6, 7, 8, 9	ICP-OES
	3	ICP-MS
Mg	1, 2	GD-MS
	3	ICP-MS
	4, 5, 6, 7, 8	ICP-OES
P	1, 2	GD-MS
	3	ETV-ICP-OES
	4, 5	ICP-OES
	6, 7	Spectrophotometry
S	1, 3	ICP-OES
	2	GD-MS
	4	Combustion/iodometric titration
Si	1	GD-MS
	2, 3	ICP-OES
Ti	1, 5, 6, 7	ICP-OES
	2	GD-MS
	3	ICP-MS
Zr	1, 5, 7, 8, 9	ICP-OES
	2	ICP-MS
	3, 6	GD-MS
	4	INAA

Abbreviations: ET AAS – Electrothermal atomic absorption spectrometry
ETV-ICP-OES – Inductively coupled plasma - optical emission
spectrometry plasma after electrothermal vaporisation
FAAS – Flame atomic absorption spectrometry
GD-MS – Glow discharge mass spectrometry
ICP-MS – Mass spectrometry with inductively coupled plasma
ICP-OES – Inductively coupled plasma - optical emission spectrometry
INAA – Instrumental neutron activation analysis

Instructions for Use

Before use, the surface of the material must be prepared by milling or turning on a lathe. For wet chemical analysis chips have to be prepared by turning or milling of the sample surface.

Transport and Storage

The material should be stored in a dry and clean environment at room temperature (approx. 20 °C). Transport under normal ambient conditions.

Technical Report

A detailed technical report describing the analysis procedures and the treatment of the analytical data used to certify BAM-M384a is available on request or can be downloaded from BAM website (www.bam.de/en/fachthemen/referenzmaterialien/index.htm).

Accepted as BAM-CRM on 23-01-2014

BAM Bundesanstalt für Materialforschung und -prüfung

Prof. Dr. U. Panne
Head of Department 1
Analytical Chemistry;
Reference Materials

Dr. S. Recknagel
Head of Division 1.6
Inorganic Reference Materials

This Reference Material is offered by:

BAM Bundesanstalt für Materialforschung und -prüfung
Richard-Willstätter-Str. 11, 12489 Berlin

Phone: +49 30 8104 2061
Fax: +49 30 8104 1117

Email: sales.crm@bam.de
Internet: www.webshop.bam.de