in cooperation with the WG 'Copper'
of the Committee of Chemists of GDMB

ausverkauft / out of stock

CERTIFICATE OF ANALYSIS

ERM®-EB385

Pure copper

SPECIMEN

Certified Values		
	Certified value [1]	Uncertainty [2]
Element	Mass fraction in mg/kg	
Ag	28.6	± 0.8
Al	28.6	± 2.5
As	11.4	± 0.8
Bi	5.81	± 0.17
Cd	5.8	± 0.3
Co	6.93	± 0.15
Cr	9.81	± 0.20
Fe	45.4	± 1.4
Mg	29.1	± 1.3
Mn	10.1	± 0.2
Ni	11.9	± 0.8
P	12.9	± 1.0
Pb	11.3	± 0.5
S	31.3	± 1.5
Sb	19.1	± 0.8
Se	7.2	± 0.5
Sn	18.0	± 0.9
Te	10.0	± 0.4
Ti	3.83	± 0.17
Zn	58	± 4

[1] Unweighted mean value of the means of accepted sets of data (at least 4 but usually 6), each set being obtained in a different laboratory and/or a different method of measurement. The values are traceable to the SI (Système International d'Unités) via calibration using sufficiently pure substances of known stoichiometry.

[2] Estimated expanded uncertainty *U* with a coverage factor of about *k*=2, corresponding to a level of confidence of 95 %, as defined in the Guide to the expression of uncertainty in measurement, ISO, 1993.

This certificate is valid until 09/2053; this validity may be extended as further evidence of stability becomes available.

Date of issue: August 2003

All following pages are an integral part of the certificate.

The minimum sample size for wet chemical analysis is 0.5 g.

NOTE

European Reference Material ERM®-EB385 was originally certified as BAM-M385. It was produced and certified under the responsibility of Bundesanstalt für Materialforschung und –prüfung (BAM) in cooperation with the Committee of Chemists of the GDMB, Gesellschaft für Bergbau, Metallurgie, Rohstoff- und Umwelttechnik according to the principles laid down in the technical guidelines of the European Reference Materials® co-operation agreement between BAM-LGC-IRMM. Information on these guidelines is available on the Internet (http://www.erm-crm.org).

Accepted as an ERM®, Berlin, 2004-04-14.

Berlin,

BAM Berlin
Department I
Analytical Chemistry;
Reference Materials
12200 Berlin, Germany

Prof. Dr. I. Nehls
(Head of Department)

BAM Berlin
Division I.1
Inorganic Chemical Analysis;
Reference Materials
12200 Berlin, Germany

Dr. R. Matschat
(Head of Division)

SPECIMEN

Indicative Values[3)]

	Indicative value [4)]	Uncertainty [5)]
Element	Mass fraction in mg/kg	
Si	7.2	± 1.5
Element	Mass fraction in mg/kg	
Zr	< 7	

[3)] Values were not certified, but given as indicative values, when the number of accepted data sets was considered to be too low, when the spread from the round robin certification was considerably larger than the state of the practice or when only 'lower as' values were reported from the round robin certification.

[4)] Unweighted mean value of the means of accepted sets of data, each set being obtained in a different laboratory and/or a different method of measurement. The values are traceable to the SI (Système International d'Unités) via calibration using sufficiently pure substances of known stoichiometry.

[5)] Estimated expanded uncertainty *U* with a coverage factor of about *k*=2, corresponding to a level of confidence of 95 %, as defined in the Guide to the expression of uncertainty in measurement, ISO, 1993.

DESCRIPTION OF THE SAMPLE

The Reference Material is available in the form of discs (40 mm diameter and 30 mm height). It is intended for establishing and checking the calibration of optical emission and X-ray spectrometers for the analysis of samples of similar materials

MEANS OF ACCEPTED DATA SETS (FOR ONE METHOD AT ONE LABORATORY, RESPECTIVELY)

Mass Fraction in mg/kg

Line no.	Ag	Al	As	Bi	Cd	Co	Cr	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Se	Sn	Te	Ti	Zn
1	26.3	21.2	-	-	5.2	6.7	9.5	42.4	24.8	9.7	10.4	11.2	10.4	28.3	17.7	6.4	16.8	9.5	3.6	41.8
2	26.6	24.0	10.4	5.5	5.4	6.7	9.6	43.0	27.2	9.8	10.9	12.5	10.6	29.8	18.0	6.8	16.8	9.5	3.7	47.3
3	27.7	27.9	10.7	5.8	5.6	6.7	9.6	43.3	28.2	10.0	11.4	12.6	10.8	30.3	19.1	7.0	17.0	9.8	3.9	54.8
4	27.9	28.0	10.8	5.8	5.8	6.8	9.6	44.2	28.7	10.0	11.5	13.0	11.2	30.6	19.3	7.1	17.3	10.0	3.9	55.2
5	28.3	28.7	10.8	5.8	5.8	7.0	9.6	44.3	29.7	10.0	11.5	13.3	11.4	32.4	19.7	7.3	17.4	10.0	3.9	55.7
6	28.4	29.0	10.9	5.9	5.8	7.1	9.7	44.9	29.8	10.1	11.8	13.4	11.5	32.9	19.7	7.4	17.9	10.1	4.0	55.9
7	28.6	29.3	11.0	5.9	5.9	7.1	9.8	45.7	29.9	10.1	12.0	14.8	11.5	33.0	20.1	7.8	19.1	10.2	4.1	59.0
8	28.6	29.5	11.2	6.2	5.9	7.1	9.8	45.8	30.1	10.1	12.0		11.7	33.0	20.2	8.0	19.3	10.4		60.6
9	28.7	29.9	11.4		6.0	7.2	9.9	45.8	30.4	10.3	12.7		11.8		20.3		19.4	10.9		60.9
10	28.7	32.2	11.4		6.7	7.2	10.1	47.5	30.5	10.3	13.0		12.1		20.3		19.7			61.3
11	28.8	35.4	11.5				10.2	47.7	30.8	10.5	14.3		12.3		20.7					61.9
12	29.2		11.6				10.2	50.2		11.1					21.3					63.2
13	29.9		11.9				10.5								22.4					65.4
14	30.2		15.1																	66.8
15	31.4																			
M :	28.60	28.62	11.41	5.81	5.76	6.93	9.81	45.36	29.05	10.13	11.91	12.93	11.33	31.26	19.86	7.18	18.03	9.98	3.83	57.86
s_M :	1.28	3.74	1.2	0.19	0.40	0.21	0.33	2.23	1.78	0.38	1.07	1.09	0.62	1.78	1.25	0.52	1.18	0.43	0.19	6.84
$\bar{s}_i$:	0.4	0.9	0.6	0.5	0.2	0.2	0.3	0.6	0.5	0.2	0.4	0.6	0.4	1.0	0.6	0.6	0.7	0.4	0.2	1.4

The laboratory mean values have been examined statistically to eliminate outlying values. Where a " - " appears in the table it indicates that an outlying value has been omitted. A data set consists of at least 4 but usually 6 single values of one laboratory. " < "-values have not been considered in statistical evaluation.

M : mean of means of data sets

s_M : standard deviation of means of data sets

$\bar{s}_i$: mean of standard deviations of data sets under repeatability conditions

numbers in *italics* are indicative values

SPECIMEN

Mass fraction in mg/kg (indicative values)

Line No.	Si	Zr
1	-	*0.1*
2	*6.0*	*0.4*
3	*6.8*	*0.6*
4	*7.4*	*1.2*
5	*8.4*	*1.6*
6		*2.1*
7		*2.2*
8		*3.1*
9		*4.0*
10		*5.7*

ANALYTICAL METHOD USED FOR CERTIFICATION

Element	Line no.	Method
Ag	1, 2, 3, 4, 5, 8, 15	Atomic emission spectrometry with inductively coupled plasma
	11*, 12**	Neutron Activation Analysis
	6, 7, 9	Flame Atomic Absorption Spectrometry
	10	Electrothermal Atomic Absorption Spectrometry
	13	Activation Analysis with High-Energy Photons
	14	Mass spectrometry with inductively coupled plasma
Al	1	Atomic emission spectrometry with inductively coupled plasma after Lanthanum precipitation
	2, 3, 4, 7, 8, 9, 11	Atomic emission spectrometry with inductively coupled plasma
	5	Atomic emission spectrometry with inductively coupled plasma after electrolytic Cu separation
	6	Electrothermal Atomic Absorption Spectrometry
	10	Mass spectrometry with inductively coupled plasma
As	1	Mass spectrometry with inductively coupled plasma
	2, 8, 9, 11, 13, 14	Atomic emission spectrometry with inductively coupled plasma
	3, 5	Atomic emission spectrometry with inductively coupled plasma after Lanthanum precipitation
	3, 12	Electrothermal Atomic Absorption Spectrometry
	6	Activation Analysis with High-Energy Photons
	7*	Neutron Activation Analysis
	10	Spectrophotometry
Bi	1, 7	Atomic emission spectrometry with inductively coupled plasma after Lanthanum precipitation
	2, 4, 5	Electrothermal Atomic Absorption Spectrometry
	3, 6	Atomic emission spectrometry with inductively coupled plasma
	8	Mass spectrometry with inductively coupled plasma
Cd	1, 2, 4, 6, 8, 9	Atomic emission spectrometry with inductively coupled plasma
	3	Flame Atomic Absorption Spectrometry
	5	Electrothermal Atomic Absorption Spectrometry
	7	Atomic emission spectrometry with inductively coupled plasma after electrolytic Cu separation
	10	Mass spectrometry with inductively coupled plasma

SPECIMEN

Co	1, 4, 6, 7	Atomic emission spectrometry with inductively coupled plasma
	2	Atomic emission spectrometry with inductively coupled plasma after electrolytic Cu separation
	3*, 9**	Neutron Activation Analysis
	5, 10	Electrothermal Atomic Absorption Spectrometry
	8	Mass spectrometry with inductively coupled plasma
Cr	1, 2, 3, 5, 7, 11, 13	Atomic emission spectrometry with inductively coupled plasma
	4	Activation Analysis with High-Energy Photons
	6	Atomic emission spectrometry with inductively coupled plasma after electrolytic Cu separation
	8	Atomic emission spectrometry with inductively coupled plasma after Lanthanum precipitation
	9**	Neutron Activation Analysis
	10	Mass spectrometry with inductively coupled plasma
	12	Electrothermal Atomic Absorption Spectrometry
Fe	1, 8	Flame Atomic Absorption Spectrometry
	2, 3, 4, 7, 11, 12	Atomic emission spectrometry with inductively coupled plasma
	5	Mass spectrometry with inductively coupled plasma
	9	Atomic emission spectrometry with inductively coupled plasma after Lanthanum precipitation
	10	Spectrophotometry
Mg	1, 2, 5, 6, 7, 8, 9, 10	Atomic emission spectrometry with inductively coupled plasma
	3	Flame Atomic Absorption Spectrometry
	4	Atomic emission spectrometry with inductively coupled plasma after electrolytic Cu separation
	11	Mass spectrometry with inductively coupled plasma
Mn	1, 2, 4, 5, 6, 7, 9, 10	Atomic emission spectrometry with inductively coupled plasma
	3	Electrothermal Atomic Absorption Spectrometry
	8	Atomic emission spectrometry with inductively coupled plasma after electrolytic Cu separation
	11	Mass spectrometry with inductively coupled plasma
	12	Activation Analysis with High-Energy Photons
Ni	1, 3, 4, 7, 9, 11	Atomic emission spectrometry with inductively coupled plasma
	2	Activation Analysis with High-Energy Photons
	5	Mass spectrometry with inductively coupled plasma
	6	Electrothermal Atomic Absorption Spectrometry
	8	Atomic emission spectrometry with inductively coupled plasma after Lanthanum precipitation
	10	Spectrophotometry
P	1, 3	Spectrophotometry
	2, 4, 5, 6, 7	Atomic emission spectrometry with inductively coupled plasma
Pb	1, 4, 8	Electrothermal Atomic Absorption Spectrometry
	2, 6, 7, 11	Atomic emission spectrometry with inductively coupled plasma
	3, 10	Atomic emission spectrometry with inductively coupled plasma after Lanthanum precipitation
	5	Atomic emission spectrometry with inductively coupled plasma after electrolytic Cu separation
	9	Mass spectrometry with inductively coupled plasma

SPECIMEN

S	1, 2	Atomic emission spectrometry with inductively coupled plasma
	3, 5	Spectrophotometry
	4, 8	Titration
	6, 7	Carrier gas hot extraction with IR-detection (gas calibration)
Sb	2	Mass spectrometry with inductively coupled plasma
	1, 11	Atomic emission spectrometry with inductively coupled plasma after Lanthanum precipitation
	3, 4, 5, 8, 13	Atomic emission spectrometry with inductively coupled plasma
	6	Spectrophotometry
	7**, 9*	Neutron Activation Analysis
	10	Activation Analysis with High-Energy Photons
	12	Electrothermal Atomic Absorption Spectrometry
Se	1, 4, 6	Atomic emission spectrometry with inductively coupled plasma
	2, 3, 8	Electrothermal Atomic Absorption Spectrometry
	5**	Neutron Activation Analysis
	7	Atomic emission spectrometry with inductively coupled plasma after Lanthanum precipitation
Si	1, 2, 4, 5	Atomic emission spectrometry with inductively coupled plasma
	3	Electrothermal Atomic Absorption Spectrometry
Sn	1, 7	Atomic emission spectrometry with inductively coupled plasma after Lanthanum precipitation
	2, 3, 4, 5, 10	Atomic emission spectrometry with inductively coupled plasma
	6	Mass spectrometry with inductively coupled plasma
	8	Electrothermal Atomic Absorption Spectrometry
	9	Activation Analysis with High-Energy Photons
Te	1, 4, 9	Electrothermal Atomic Absorption Spectrometry
	2, 3	Atomic emission spectrometry with inductively coupled plasma after Lanthanum precipitation
	5, 7	Atomic emission spectrometry with inductively coupled plasma
	6	Mass spectrometry with inductively coupled plasma
	8	Activation Analysis with High-Energy Photons
Ti	1, 2, 3, 4, 6, 7	Atomic emission spectrometry with inductively coupled plasma
	5	Electrothermal Atomic Absorption Spectrometry
Zn	1, 6, 7, 8, 10, 12, 14	Atomic emission spectrometry with inductively coupled plasma
	2*, 4**	Neutron Activation Analysis
	3	Activation Analysis with High-Energy Photons
	5, 11	Flame Atomic Absorption Spectrometry
	9	Atomic emission spectrometry with inductively coupled plasma after electrolytic Cu separation
	13	Mass spectrometry with inductively coupled plasma
Zr	1	Atomic emission spectrometry with inductively coupled plasma after electrolytic Cu separation
	2	Mass spectrometry with inductively coupled plasma
	3, 4, 5, 6, 7, 8, 9	Atomic emission spectrometry with inductively coupled plasma
	10	Activation Analysis with High-Energy Photons

* after dissolution of the sample
** solid sample

SPECIMEN

PARTICIPANTS

Bundesanstalt für Materialforschung und -prüfung (BAM), Berlin (Germany)
Laboratory I.11 (Metal Analysis)
Laboratory I.43 (Activation Analysis, Gas Analysis)
Bureau of Analysed Samples, Middlesbrough (Great Britain)
Diehl Metall Stiftung & Co KG, Röthenbach a. d. Pegnitz (Germany)
Institut für Kernchemie, University of Mainz (Germany)
Institut für NE-Metallurgie und Reinststoffe, TU Bergakademie Freiberg (Germany)
KM Europa Metal AG, Osnabrück (Germany)
MKM Mansfelder Kupfer und Messing GmbH, Hettstedt (Germany)
Montanwerke Brixlegg AG, Brixlegg (Austria)
Norddeutsche Affinerie AG, Hamburg (Germany)
Swedish Institute for Metals Research, Stockholm (Sweden)
Tréfimétaux SA, Sérifontaine (France)
Umicore, Olen (Belgium)
Wieland-Werke AG, Ulm (Germany)

INSTRUCTIONS FOR USE

Before use, the surface of the material must be cleaned by turning on a lathe.

STORAGE

The material should be stored at ambient conditions in a dry and clean environment.

TECHNICAL REPORT

A detailed technical report (in German) describing the analysis procedures and the treatment of the analytical data used to certify ERM®- EB385 is available on request.

SPECIMEN

Supply of Reference Materials by Bundesanstalt für Materialforschung und –prüfung:

Richard-Willstätter-Straße 11, 12489 Berlin, Germany

Phone: +49 30 8104 2061 e-mail: sales.crm@bam.de

Fax: +49 30 8104 1117 internet: www.bam.de